



SHANGRAO RUICHEN SEALING CO.,LTD
DONGGUAN RUICHEN SEALING CO.,LTD

Address: Road 8.Yanshan Industrial Estate, Shangrao City, 334500, Jiangxi Prov., CHINA
 Tel: +86-18024335478 E-mail: aaron@dgork.com

MATERIALS TEST REPORT

AFLAS80 BLACK (AF8001) COMPOUND

ASTM D2000 M2HK 810 A1-10 B38 EO78 EF31 F13

Press Cure		Post Cure	
Sheet : 10min 170°C		Sheet : 16 hrs200°C	
Button : 10 min 170°C		Button : 16 hrs 200°C	
ORIGINAL PROPERTIES	SPECIFICATION	TEST RESULT	ASTM TEST METHOD
HARDNESS SHORE A	80°±5	80	D2240
TENSILE STRENGTH, MPA, MIN	≥10	10.96	D412
ULTIMATE ELONGATION, %, MIN	≥150	248.38	D412
SPECIFIC GRAVITY (g/cm ³)		1.72	D297
HEAT RESISTANCE 70 H . AT 250°C (A1-10)			D573
CHANGE IN HARDNESS, POINTS	+10	+3	
CHANGE IN TENSILES STRENGTH, %	-25	-15.28	
CHANGE IN ULTIMATE ELONGATION,MAX %	-25	-5.68	
COMPRESSION SET, MAX, 22H AT 200°C (B38)	≤30	16.88	D395
FLUID RESISTANCE FUEL.101. 70H AT 200°C (EO78)			D471
CHANGE IN HARDNESS, POINTS	-15~+5	-8.5	
CHANGE IN TENSILES STRENGTH, MAX %	-40	-22.78	
CHANGE IN ULTIMATE ELONGATION,MAX %	-20	-9.63	
CHANGE IN VOLUME %	0~+15	+8.96	
FLUID RESISTANCE FUEL C, 70H AT 23°C (EF31)			D471
CHANGE IN HARDNESS, POINTS	±5	-3	
CHANGE IN TENSILES STRENGTH, MAX %	-25	-15.27	
CHANGE IN ULTIMATE ELONGATION,MAX %	-20	-10.29	
CHANGE IN VOLUME %	0~+10	+2.98	
LOW-TEMPERATURE BRITTLENESS NONBRITTLE AFTER 3MIN AT -10°C(F13)	NONBRITTLE	PASS	D2137

Remark:

1. The data are based on testing slabs I buttons and are for reference purpose only..
2. Our compound can meet above -mentioned ASTM 2000 Spec.
3. This information is, to the best of our knowledge, accurate reliable to the date indicated.
4. The above mentioned data have been obtained by tests we consider as reliable, We don't assure that
 - the same results can be obtained other laboratories, using different conditions by the preparation and
 -evaluation of the samples.

Approved By	Frankie Fang	Checked By:	Yunli Tu	Tested By:	Jianjun Zhu
-------------	---------------------	-------------	-----------------	------------	--------------------